

EE CORE

TYPE	FIG.	Dimensions(mm)					
		A	B	C	D	E	F
EE5/5/2	1	5.25±0.2	2.65±0.15	1.95±0.1	1.35±0.1	3.8min	2.0±0.15
EE6.3/6.7/1.2	1	6.3±0.3	3.35±0.1	1.2±0.2	1.75±0.2	4.2min	2.1±0.1
EE8.3/8/4	1	8.7±0.3	4.1±0.2	3.9±0.2	1.85±0.15	6.1min	3.1±0.2
EE10/11/5	1	10.2±0.3	5.5±0.15	4.85±0.2	2.5±0.15	7.5min	4.3±0.15
EE10/11/10	1	10.5±0.5	5.5±0.15	9.8±0.3	2.4±0.3	7.6min	4.3±0.2
EE12/13/4	1	11.9±0.4	6.5±0.3	3.7±0.2	2.5±0.2	8.6min	4.9±0.3
EE13/13/4	1	12.7±0.35	6.35±0.15	3.6±0.2	3.6±0.2	8.8min	4.65±0.15
EE13/12/6	1	13.0±0.4	6.0±0.15	6.0±0.15	2.6±0.2	9.8min	4.7±0.3
EE13/13/6	1	13.2±0.4	6.3±0.3	6.0±0.3	2.7±0.3	10.0min	4.7±0.3
EE13/13/10	1	13.2±0.4	6.3±0.3	9.8±0.3	2.7±0.3	9.8min	4.7±0.3
EE16/12/5	1	16.1±0.6	6.1±0/-0.3	4.7±0/-0.4	4.7±0/-0.3	11.45min	3.8±0.2
EE16/12/7	1	16.0±0.35	6.0±0.15	7.2±0.2	4.55±0.2	11.3min	3.85±0.15
EE16/14/7	1	16.0±0.5	7.3±0.3	6.7±0.3	4.0±0.3	11.8min	5.2±0.3
EE16/15/5	1	16.0±0.5	7.3±0.3	5.0±0.3	4.0±0.3	11.8min	5.2±0.3
EE16/16/5	1	16.2±0.6	8.1±0.3	4.5±0.3	4.5±0.3	11.4min	5.9±0.3
EE16/16/7	1	16.0±0.5	8.2±0.2	7.0±0.3	4.6±0.3	11.2min	6.0±0.2
EE16/16/8	1	16.0±0.7/-0.5	8.2±0/-0.3	8.2±0/-0.3	4.7±0/-0.3	11.3±0.6/-0	5.7±0.4/-0
EE16/25/5	1	16.0±0.4	12.5±0.2	4.8±0.2	4.0±0.2	11.7min	10.35±0.2
EE19/16/5	1	19.0±0.4	8.0±0.15	4.8±0.2	4.75±0.2	13.8min	5.8±0.15
EE19/16/7	1	19.2±0.3	8.2±0.2	6.7±0.3	4.7±0.2	14.4min	5.9±0.2
EE19/16/10	1	19.2±0.5	8.1±0.3	9.5±0.3	4.6±0.3	14.2min	5.8±0.3
EE19/20/5	1	19.1±0.5	9.9±0.25	5.0±0.5	4.55±0.5	14.0min	7.6±0.15
EE19/27/5	1	19.1±0.3	13.55±0.25	5.0±0.2	4.7±0.3	14.0min	11.15±0.35
EE20/20/6	1	20.0±0.5	10.1±0.3	5.7±0.3	5.7±0.3	14.1min	7.6±0.3
EE20/20/9	1	20.0±0.6	9.9±0.2	8.8±0.25	5.7±0.2	14.1min	7.2±0.2
EE20/20/11	1	20.0±0.4	10±0.15	10.8±0.3	5.7±0.2	14.1min	7.2±0.15
EE20/21/7	1	20.5±0.5	10.7±0.3	7.0±0.3	5.0±0.3	14.7min	7.0±0.3
EE20/28/5	1	20.1±0.5	13.9±0.3	4.8±0.3	4.8±0.3	14.6min	11.7±0.3
EE22/19/6	1	22.4±0.5	9.5±0.4	5.65±0.25	5.65±0.25	16.0min	5.6±0.4
EE22/30/6	1	22.0±0.4	15.0±0.4	5.75±0.25	5.75±0.25	15.6min	11.3±0.2
EE22/44/5	1	22.2±0.4	22.2±0.4	4.7±0.3	5.8±0.3	15.6min	18.2±0.2


EE CORE

FIG.1

Cl (mm ⁻¹)	Ae (mm ²)	Le (mm)	Ve (mm ³)	AL±25%(nH/N ²)						Weight g/PRS
				FW40	FW44	FW95	FW5K	FW7K	FW10K	
5.01	2.53	12.68	32.1	250	260	290	400	530	960min	0.20
6.17	2.31	14.27	33.0	200	210	240				0.18
2.75	7.00	19.20	134.0	550	555	650	1200	1300	1500min	0.70
2.23	11.81	26.30	310.6	800	850	1000	1700	2000	2300min	1.50
1.1	23.10	26.40	611.6	1900	1900					3.20
3.19	9.25	29.55	352.3						3000min	1.80
2.34	12.68	29.62	375.5	800	800	1000	1530	1780	2240min	1.90
1.92	15.90	30.61	486.8	980	980	1150	1500	1750	2150min	1.20
1.86	16.20	30.20	586.0	1000	1000	1500	2200	2700	3100min	2.70
1.13	26.46	29.95	975.0	2200	2330					3.50
1.52	19.28	29.39	566.8	1160	1200	1450				2.92
0.93	31.62	29.36	928.3	2010	2050	2500				4.80
1.44	26.20	37.90	993.0	1130	1220	1500				4.60
1.8	19.00	34.80	670.0	1100	1170	1250	2400	2800	3200min	3.30
1.87	20.10	37.60	754.0	1000	1070	1320	2300	2800	3200min	3.90
1.05	34.20	38.40	1033.4	1200						5.80
1.03	36.33	37.56	1364.7	1900	1950	2400				6.86
2.78	20.01	55.67	1114.0	800	770					5.10
1.79	22.28	39.81	886.9	1150	1200	1450	1950	2300	3300min	4.40
1.34	30.30	40.80	1236.0	1500	1520	1850				6.30
0.9	44.50	39.90	1777.5	1700	2250	2800				9.20
2.08	22.90	47.60	1090.0	950	1060	1320				6.80
2.78	22.40	62.20	1393.0	830	860	1100	1800	2300	2800min	7.00
1.38	31.00	43.00	1340.0	1250	1600	1950				7.50
0.96	48.06	46.32	2226.0	2170	2220	2800				
0.77	60.46	46.39	2804.6	2800	2900	3600				14.2
1.20	39.29	47.09	1850.2	1600	1650	2070	3600	4200	5800min	9.70
2.55	24.50	62.74	1541.8	860	880	1130	2800	3500	4200min	8.40
1.29	31.92	41.22	1749.2	1790	1900	2350	3900	4700	5600min	7.00
1.82	35.00	63.60	2220.0	1300	1230	1570	2800	3500	4200min	11.1
3.15	29.60	93.20	2757.0	650	750	970				13.80